

10 Rec'd PCT/PTO

FEB 2005

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 February 2004 (12.02.2004)

PCT

(10) International Publication Number
WO 2004/013920 A2

- (51) International Patent Classification⁷: **H01L 51/20**
- (21) International Application Number:
PCT/GB2003/003292
- (22) International Filing Date: 30 July 2003 (30.07.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0218202.0 6 August 2002 (06.08.2002) GB
- (71) Applicant (*for all designated States except US*): **AVECIA LIMITED** [GB/GB]; Hexagon House, Blackley, Manchester M9 8ZS (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **VERES, Janos** [HU/GB]; P.O. Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB). **OGIER, Simon, Dominic** [GB/GB]; Hexagon House, Blackley, Manchester M9 8ZS (GB). **YEATES, Stephen, George** [GB/GB]; PO Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB).
- (74) Agents: **PARLETT, Peter et al.**; Avecia Limited, Intellectual Property Group, P.O. Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: ORGANIC LIGHT EMITTING DIODES

(57) Abstract: This invention relates to organic light emitting diodes (OLEDs) and to methods for their manufacture. The invention provides an OLED element or display, which enables contrast to be produced in an image. In accordance with the invention a layer of ink is patterned as a blocking layer between two OLED layers. The ink reduces or prevents conduction, i.e. movement of charge, between the two OLED layers in that area of the device. The ink may be dark in color, e.g. black, to increase the contrast ratio of the OLED. The blocking layer is provided between any two layers in the OLED and blocks the charge movement in these areas. The blocking layer may comprise a multiplicity of ink dots, the density of which determines the extent to which conduction is hindered. The blocking layer may be produced as a "grey-scale" pattern wherein the density of dots is varied across the pattern.

WO 2004/013920 A2

BEST AVAILABLE COPY

ORGANIC LIGHT EMITTING DIODES

5 This invention relates to organic light emitting diodes (OLEDs), to methods for their manufacture and to their uses.

OLEDs have been attracting growing interest over the past decade. OLEDs are devices that generally comprise an organic electroluminescent material sandwiched between two electrodes. When an electrical current is applied the OLED radiates light generated by recombination of electrons and holes in the electroluminescent material.

10 Plastic OLED devices based on light emitting polymers (LEP) or electroluminescent organic molecules make it possible to produce low cost, large area displays on flexible substrates, especially by solution coating. Low cost manufacturing, however, requires printing techniques that take advantage of the solution coatability of OLEDs.

The present invention provides an OLED element or display which enables

15 contrast to be produced in an image and a method for the manufacture thereof.

In accordance with the present invention a layer of ink is patterned as a blocking layer between two OLED layers. The ink reduces or prevents conduction, i.e. movement of charge, between the two OLED layers in that area of the device, thus providing contrast in the image. The ink may be coloured. In one embodiment, preferably the ink is dark in

20 colour, e.g. black, to increase the contrast ratio of the OLED. The ink may be coloured so as to provide a coloured background to the image. In this way, in one embodiment, areas in which the ink pattern exists may be of one colour whereas the illuminated image may have a different colour.

In more detail, in one aspect, the present invention provides a method of forming

25 an OLED element or display having two or more OLED layers, which method comprises providing a blocking layer by printing with an ink in a desired pattern between two of the OLED layers, whereby, in use, conduction across the OLED element or display is reduced in the area of the pattern.

In one embodiment, the method comprises the steps of providing a first OLED

30 layer, providing the blocking layer on top of the first OLED layer and providing a second OLED layer on top of the blocking layer.

The OLED layers are defined hereinafter.

The blocking layer is provided between any two layers in the OLED and blocks the charge movement in the area of the pattern. The blocking layer is typically located

35 between the electroluminescent layer and either the anode or cathode of the OLED element or display. The blocking layer may directly contact the anode or the cathode. Alternatively, there may be present one or more additional layer(s) on the anode or cathode and the blocking layer may instead directly contact the additional layer. The additional layer(s) may comprise, for example, a hole injection layer or electron injection

40 layer, such as a conductive material, e.g. a conductive polymer. The blocking layer may directly contact the electroluminescent layer or, alternatively, there may be one or more

additional layer(s), such as hole or electron transport layer(s), between the blocking layer and the electroluminescent layer.

The blocking layer pattern may comprise a multiplicity of discrete points of the ink, such as dots, the density of which (i.e. the number of points per unit area) determines the extent to which conduction is hindered. The points may be each less than about 100 μm in size. The pattern may comprise regions with different densities of the discrete points such that some regions of the pattern may on average restrict conduction more than other regions. For example, regions of the pattern comprising a higher density of dots may restrict conduction to a greater extent whereas regions with a lower density of dots may restrict conduction to a correspondingly lesser extent. Such "grey-scale" patterning can be used to provide contrast in an image without need for sophisticated driving electronics such as active matrix transistor backplanes thus greatly reducing the cost of providing contrast in OLED displays. The grey-scale patterning, in use, can produce the appearance of a three-dimensional image on a two-dimensional OLED display.

The OLED elements may be used, for example, to manufacture multicolour displays, small or large area signs, logos or illuminating features.

The blocking layer of the desired pattern is preferably formed using an ink by printing. The term ink is used because of its capability of being printed rather than to mean that it must contain a colorant. However, the ink may contain colorant to increase the contrast ratio. Any material capable of being printed and which is preferably non-conducting may be used as the ink. The ink is preferably insoluble in the medium used to deposit earlier and/or subsequent OLED layer(s), i.e. underlying or overlying OLED layer(s). The ink medium is preferably a liquid which does not dissolve the layer on which the ink is printed. The ink medium can be either aqueous or non aqueous. For example, a water based ink is suitable on polymer surfaces that are insoluble in water, e.g. polyesters. The ink may be flexible in composition and include flow and other additives. When used with screen-printing applications, the ink can have a very high viscosity, up to 90,000 cp, preferably up to 70,000 cp, and more preferably between 500 and 10,000 cp. But when used with ink-jet printing, the ink viscosity is preferably in the range from about 0.7 to 100 cp, and more preferably from about 3 to 40 cp. The ink preferably has a surface tension from 20 to 70 dynes/cm, more preferably 20 to 60 dynes/cm. This will be governed both by the mode of printing, choice of inkjet printing head and the surface energy of the surface to be printed. Since good edge acuity is required then the surface tension of the ink relative to the substrate is preferably from 20 to 110deg and more preferably 40 to 80deg. For an inkjet ink the contact angle with the nozzle plate is preferably from 10 to 150 deg.

The ink may be either polar or nonpolar and the liquid medium of the ink preferably has a boiling point from 40°C. to 300°C. Preferred liquid media include, but are not limited to, water, alcohol, dioxane, glycols, cyclic amides, toluene, chloroform, tetrahydrofuran, dichlorobenzene, 1,2-dichloroethane, and xylene. The ink preferably

contains from 50% to 99.8% liquid medium, by weight. Liquid medium mixtures are preferred to help control ink application properties such as latency, substrate wetting and drying time.

5 The ink may further comprise a colorant, a polymeric binder and/or functional additives which are used to modify the ink viscosity, surface tension, and latency. The ink preferably comprises a colorant to improve contrast in the image produced by the OLED element or display. A colorant may be included which gives the areas patterned by the ink a desired colour, different to the illuminated image. Suitable colorants for the ink composition include dyes or pigments such as carbon black. Non-black colorants may be
10 used. Suitable polymeric binders for the ink composition include but not limited to acrylics, polyurethanes or silanes.

The ink may be deposited by a direct printing technique. Suitable direct printing techniques include: ink-jet printing, screen printing, microcontact printing, stamping, soft lithography or electrophotographic printing using a liquid or solid toner. The term ink used
15 herein includes toner. In each case the ink is formulated to the appropriate viscosity, rheology and surface tension for the specific printing process. Ink-jet printing is particularly preferred. The use of ink-jet printing is advantageous because the same ink formulation and ink-jet head may be used, followed by the same chemical or mechanical process for the step, for the patterning of different layers thereby simplifying the hardware required.
20 The printed ink is preferably thicker than the layer subsequently deposited onto it, this improves the efficiency of the step. The pattern is typically from 100 nm to 100 μ m thick, preferably from 1 μ m to 50 μ m.

The OLED layer(s) to be deposited may be applied by a variety of coating and printing techniques. Examples include solution-, spin-, spray-, dip-, web-, die- or
25 evaporation coating; electroless deposition and ink-jet printing, screen printing, microcontact printing, stamping or soft lithography. When the OLED layer is deposited by ink-jet printing, selective deposition on different areas is possible. For example, red, green and blue electroluminescent materials may be deposited on different areas.

The thickness of each OLED layer or multiplicity of layers may be from 1nm (in
30 case of a monolayer) to 10 μ m, preferably from 1nm to 1 μ m, more preferably from 1nm to 500nm. The preferred deposition technique for the OLED layer(s) is a liquid coating technique, more preferably spin-, die- or spray-coating.

The use of a patterned blocking layer enables the OLED layer(s) to be applied with good uniformity of thickness. Even if variations in blocking layer thickness occur across
35 the device the subsequent OLED layer(s) can be applied uniformly across the device, e.g. by a form of coating. Since the blocking layer provides a pattern, the OLED layer(s) can be simply coated on the device. The uniformity of OLED layer(s) yields improved image quality.

Various substrates may be used for the fabrication of OLEDs, plastics materials
40 are preferred and examples include alkyd resins, allyl esters, benzocyclobutenes,

butadiene-styrene, cellulose, cellulose acetate, epoxide, epoxy polymers, ethylene-chlorotrifluoro ethylene, ethylene-tetra-fluoroethylene, fibre glass enhanced plastic, fluorocarbon polymers, hexafluoropropylenevinylidene fluoride copolymer, high density poly-ethylene, parylene, polyamide, polyimide, polyaramid, polydimethylsiloxane, polyethersulphone, polyethylene, polyethylenenaphthalate, polyethyleneterephthalate, polyketone, polymethylmethacrylate, polypropylene, polystyrene, polysulphone, polytetrafluoroethylene, polyurethanes, polyvinylchloride, silicone rubbers, silicones. Preferred substrate materials are polyethyleneterephthalate, polyimide, and polyethylenenaphthalate. The substrate may be any plastic material, metal or glass coated with the above materials. The substrate should preferably be homogenous to ensure good pattern definition.

The wetting of the ink formulation may be optimised by the surface treatment of the substrate, for example, by plasma treatment. Such treatment may also be used to enhance adhesion of the layer to be patterned to the substrate or improve edge acuity. As a result, the of the ink together with the layer above may be more efficient. The technique can be further optimised by using intermediate layers coated between the ink pattern and the layer to be patterned. Such layers can be used as barriers stopping the diffusion of ink into other layers.

The OLED comprises at least an anode (electron blocking layer or hole injection electrode), a cathode (hole blocking layer or electron injection electrode) and an electroluminescent layer, each of which may constitute an OLED layer as referred to herein. The OLED optionally comprises other layers such as a hole injection layer(s), a hole transport layer(s), an electron injection layer(s), an electron transport layer(s), a dopant or an insulator(s), all or any of which may constitute an OLED layer as referred to herein.

The electroluminescent layer is made up of substantially organic or organometallic electroluminescent materials. Suitable materials include organic photo- or electroluminescent, fluorescent and phosphorescent compounds of low or high molecular weight. Suitable low molecular weight compounds include, but are not limited to, substituted 9,9' spirobifluorenes (EP 0676461), Alq3 (an aluminum complex formed by coordination of three molecules of hydroxyquinoline with an aluminum atom), lanthanide complexes such as those of europium and ytterbium (WO 9858037), triplet emitters such as Ir[2-PhPy]₃. Suitable high molecular weight materials include polymers preferably those having substantially conjugated backbone (main chain), such as polythiophenes, polyphenylenes, polythiophenevinylenes, polyphenylenevinylenes, polyalkylfluorenes. In the present invention the term polymer includes homopolymer, copolymer, terpolymer and higher homologous as well as oligomers. Examples of such materials are given in US 5708130, WO97/39082, WO96/10598.

The electroluminescent layer preferably has an average thickness of from 50 to 200nm, more preferably from 60nm to 150nm.

The electron blocking layer (hole injection electrode) is suitably made of a metal or an alloy having a high work function such as Au, Pt, Ag. Preferably, a more transparent electron blocking layer (hole injection electrode) material such as an indium tin oxide (ITO) is used. Conductive polymers such as polyaniline (PANI) and a poly-3,4-ethylenedioxythiophene (PEDOT) are also suitable transparent hole-injection electrodes. Preferably, the electron blocking layer (hole injection electrode) has a thickness of from 50 to 300nm.

Hole-injecting and hole-transporting layer materials include soluble phthalocyanine compounds, triarylamine compounds, electroconductive polymers, perylene compounds, and europium complexes.

Electron-injecting and electron-transporting layer materials include Alq3, azomethine zinc complexes, and distyrylbiphenyl derivatives. These are however not exhaustive.

The electron injection electrode is preferably made of a metal or an alloy having a low work function, such as Yb, Ca, Al, Mg:Ag, Li:Al, Ba or is a laminate of different layers such as Ba/Al or Ba/Ag electrode.

Dopants used in the invention may be compounds such as 3-(2-Benzothiazolyl)-7-diethylaminocoumarin (Coumarin 6), europium complexes, ruthenium complexes, Rhodamine salts, platinum complexes, iridium complexes and Nile red although this list is not exhaustive.

Insulators used in the invention may be inorganic or organic or a composite of the two. It is preferred that the insulator is solution coated enabling ambient processing. When the insulator is being patterned, it may perform the function of a blocking layer between OLED materials. The insulator may be any organic polymer or polymer precursor, optionally containing inorganic particles. The insulator can be spray-, dip-, web- or spin coated or deposited by any liquid coating technique. Any liquid carrier may be employed as long as it does not dissolve the ink.

The invention will now be further described by way of example and with reference to the accompanying drawings in which:

Figure 1 shows the patterning of an ink which is used to block the movement of charge into the electroluminescent layer;

Figure 2(a) shows a pattern for a blocking layer to be printed between two layers of the OLED device to produce a simple grey-scale image;

Figure 2(b) shows the resultant grey-scale image in the operating OLED produced by the pattern in Figure 2(b);

Figure 3 shows a pseudo 3-D image by use of grey-scale shading;

Figure 4 shows a pattern printed onto PEDOT using ink that serves as a blocking layer;

Figure 5 shows the areas of PEDOT from Figure 4 which had no ink upon them emitting light with all other areas blocked by the ink-jet printed layer;

Figure 6(a) shows a grey-scale test pattern for a blocking layer;

Figure 6(b) shows a shadow mask geometry;

Figure 7 shows a grey-scale OLED device produced using the grey-scale test pattern and shadow mask of Figures 6(a) and (b);

Figure 8 shows a "pseudo 3-D" grey-scale pattern for a blocking layer; and

- 5 Figure 9 shows an image of a 3-D logo produced using the grey-scale shading of the pattern in Figure 8.

Figure 1 shows the patterning of an ink which is used to block the movement of charge into the electroluminescent layer, thereby allowing a patterned OLED to be constructed. A layer of metal (42) forming an anode is deposited on a substrate (41) by evaporation or sputtering. A conductive polymer layer (43) is then applied by spin coating. The blocking ink (44) is patterned in areas where the device is not to emit light. Following this the electroluminescent layer (45) is deposited by spin coating or evaporation on top of the ink. Finally a cathode layer is deposited (46). Alternative examples can be envisaged where the blocking ink is deposited upon a different layer of the device such as the electroluminescent layer or anode. The use of the blocking layer in areas where the device is not to emit light improves the contrast between the emitting areas and the "background". If the ink is coloured, preferably a dark colour, the contrast is further improved.

In a further embodiment of the invention a blocking layer is used within the OLED in such a way that the emission is modulated progressively from dark to bright across the area of the OLED device. The blocking layer is printed in a series of discretely placed ink drops (or electrophotographic toner), typically each less than 100 μm in size, the density of which determines the output brightness of the OLED in that area (see scheme in Figures 2(a) and (b)). In Figure 2(a), the blocking layer is printed with a high dot density at the top of the display changing progressively to a low dot density at the bottom of the display. This "grey-scale" patterning of the blocking layer allows contrast to be created in an image (as shown in Figure 2(b)) without the need for sophisticated driving electronics such as active matrix transistor backplanes. As such this will dramatically reduce the cost of producing grey-scale images in OLEDs.

Grey-scale patterning is advantageous in a display application as it allows a depth of image or "pseudo 3-D image" to be conveyed to the viewer from a 2 dimensional source i.e. flat plane. An example of this application is shown in Figure 3 in which the "AVECIA" name is presented as a pseudo 3-D image by use of grey-scale shading. The "front" of the letters is produced by areas with no or low dot density so it appears bright and the "side" of the letters is produced by areas with higher dot density so they appear darker, thus giving the impression of 3-D.

Uses of grey-scale patterning of OLEDs are numerous and include, without limiting to these examples, company logos, user interfaces on machines, displays on electronic devices, artwork, light-emitting wallpaper etc.

Example 1 – Simple blocking layer

An ITO coated polyester substrate was cleaned in an air plasma for 20s using a voltage of 5kV. Following this, a water dispersion of poly(3,4-ethylenedioxythiophene)/poly(styrenesulfonate) (PEDOT) (Baytron P CH8000) was deposited and spun at 1000 rpm for 20s to give a layer of approximately 100nm in thickness. This was dried in an oven at 100 °C for 5 minutes. The pattern (Figure 4) was printed onto the PEDOT using ink that served as a blocking layer. After printing on the PEDOT the sample was baked at 100 °C for 1 minute. A quantity of "super yellow" PPV (Covion SY-17) formulated at 0.5% (wt.) in toluene was deposited on the substrate and spun at 1000 rpm for 30s to give an approximately 70 nm layer. The sample was dried at 100 °C for 20 minutes to evaporate the solvent. An aluminium cathode was deposited onto the sample by thermal evaporation of the metal, through a plastic shadow mask, under vacuum. To test the efficiency of patterning, contacts were made to the ITO and aluminium and the appropriate connections made to a function generator which supplied a 20V square wave signal at low frequency (~5 Hz). The areas of PEDOT which had no ink upon them emitted light and the remaining areas were blocked by the ink-jet printed blocking layer as shown in Figure 5. This demonstrates a method whereby an OLED is patterned using a standard inkjet ink but has the added advantage of creating extra contrast due to the black background.

20

Example 2 - Patterning grey-scale images

An ITO coated polyester substrate was cleaned in an air plasma for 30s using a voltage of 5kV. Following this, a water dispersion of poly(3,4-ethylenedioxythiophene)/poly(styrenesulfonate) (PEDOT) (Baytron P CH8000) was deposited and spun at 1000 rpm for 20s to give a layer of approximately 100nm in thickness. This was dried in an oven at 100 °C for 5 minutes. The grey-scale pattern (Figure 6(a)) was printed onto the PEDOT using ink that served as a blocking layer. After printing on the PEDOT the sample was baked at 100 °C for 1 minute. A quantity of "super yellow" PPV (Covion SY-17) formulated at 0.5% (wt.) in toluene was deposited on the substrate and spun at 1000 rpm for 30s to give an approximately 70 nm layer. The sample was dried at 100 °C for 20 minutes to evaporate the solvent. The aluminium cathode was deposited onto the sample by thermal evaporation of the metal, through a plastic shadow mask as shown in Figure 6(b), under vacuum. This produced an aluminium cathode in a horizontal strip. To test the efficiency of patterning, contacts were made to the ITO and aluminium and the appropriate connections made to a power supply. Applying a voltage to the device resulted in light being emitted. The brightest area corresponded to the area where little or no ink was printed and then the image became progressively darker across the device until no light was emitted from the area which had the most ink printed. The resulting image of the working device can be seen in Figure 7 . The far left of the

35

illuminated device in Figure 7 corresponds to the area that received little or no ink and progressively towards the far right the density of ink increases and so appears dark.

Example 3

- 5 A further device was made using the same method as Example 2 but where the ink pattern was printed in a "pseudo 3-D" pattern as shown in Figure 8. An image of the working device can be seen in Figure 9.

CLAIMS

1. A method of forming an OLED element or display having two or more OLED layers, which method comprises providing a blocking layer by printing with an ink in a
5 desired pattern between two of the OLED layers, whereby, in use, conduction across the OLED element or display is reduced in the area of the pattern.
2. A method of forming an OLED element or display as claimed in claim 1 wherein the ink is coloured to increase contrast.
- 10 3. A method of forming an OLED element or display as claimed in claim 1 or 2 wherein the blocking layer is located between an electroluminescent layer and either an anode or cathode of the OLED element or display.
- 15 4. A method of forming an OLED element or display as claimed in any one preceding claim wherein the blocking layer pattern comprises a multiplicity of discrete points of ink.
5. A method of forming an OLED element or display as claimed in claim 4 wherein the discrete points of ink are less than about 100 μm in size.
- 20 6. A method of forming an OLED element or display as claimed in claim 4 or 5 wherein the pattern comprises regions with different densities of the discrete points.
7. A method of forming an OLED element or display as claimed in any one preceding
25 claim wherein the ink is insoluble in the medium used to deposit underlying and/or overlying OLED layers.
8. A method of forming an OLED element or display as claimed in any one preceding
30 claim wherein the ink comprises a medium which is a liquid which does not dissolve the layer on which the ink is printed.
9. A method of forming an OLED element or display as claimed in any one preceding
35 claim wherein the ink further comprises a colorant, a polymeric binder and/or functional additives.
10. A method of forming an OLED element or display as claimed in any one preceding
40 claim wherein the ink is deposited by a direct printing technique selected from ink-jet printing, screen printing, microcontact printing, stamping, soft lithography or electrophotographic printing using a liquid or solid toner.

11. A method of forming an OLED element or display as claimed in claim 10 wherein the ink is deposited by ink-jet printing.
12. A method of forming an OLED element or display as claimed in any one preceding claim wherein the ink blocking layer is thicker than the OLED layer(s) subsequently deposited onto it.
13. A method of forming an OLED element or display as claimed in any one preceding claim wherein the ink blocking layer thickness is from 100 nm to 100 μ m thick.
14. A method of forming an OLED element or display as claimed in any one preceding claim wherein the OLED layer(s) to be deposited are independently applied by a coating or printing technique selected from solution-, spin-, spray-, dip-, web-, die- or evaporation coating; electroless deposition and ink-jet printing, screen printing, microcontact printing, stamping or soft lithography.
15. A method of forming an OLED element or display as claimed in any one preceding claim wherein the wetting of the ink includes a surface treatment of the layer on which the ink is deposited.
16. An OLED element or display obtainable by a method as claimed in any one preceding claim.
17. An OLED display as claimed in claim 16 which, in use, produces a pseudo 3-D image.

5




Figure 1

Fig. 2(a)




Fig. 2(b)

Figures 2 (a) and (b)




Figure 3



Figure 4



Figure 5





Figure 6(a)



Aluminium deposited in these areas

Figure 6(b)




Figure 7




Figure 8



Figure 9

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03292

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L51/20 H01L51/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y A	WO 99/21233 A (YANG YANG ; UNIV CALIFORNIA (US)) 29 April 1999 (1999-04-29) page 9, line 7 -page 10, line 14 page 11, line 29-31 page 13, line 7 -page 14, line 23	1-6, 9-11, 14, 16 7, 8, 17
Y A	US 5 949 186 A (KAWAMI SHIN ET AL) 7 September 1999 (1999-09-07) abstract column 2, line 8-17, 27-37, 51-65 column 3, line 13-27	1-6, 9-11, 14, 16 5
	----- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

8 April 2004

Date of mailing of the international search report

29/04/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Laere, A

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03292

C(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 09, 13 October 2000 (2000-10-13) -& JP 2000 173777 A (FUTABA CORP), 23 June 2000 (2000-06-23) abstract ---	1,3,14, 16
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 01, 29 January 1999 (1999-01-29) -& JP 10 270173 A (KIDO JUNJI; AIMESU:KK), 9 October 1998 (1998-10-09) abstract ---	1,3,14, 16
A	EP 0 880 303 A (SEIKO EPSON CORP) 25 November 1998 (1998-11-25) page 14, line 12-16 ---	15
A	EP 1 103 590 A (SHARP KK) 30 May 2001 (2001-05-30) paragraph '0042! ---	7,8
A	EP 1 195 736 A (EASTMAN KODAK CO) 10 April 2002 (2002-04-10) the whole document ---	1-17
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 04, 30 April 1996 (1996-04-30) -& JP 07 335383 A (SEIKOSHA CO LTD), 22 December 1995 (1995-12-22) abstract -----	1-3,9,10

INTERNATIONAL SEARCH REPORT

PCT/GB 03/03292

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9921233	A	29-04-1999	AU 725148 B2	05-10-2000
			AU 1084699 A	10-05-1999
			CA 2306948 A1	29-04-1999
			CN 1280708 T	17-01-2001
			EP 1029369 A1	23-08-2000
			JP 2001521269 T	06-11-2001
			WO 9921233 A1	29-04-1999
US 5949186	A	07-09-1999	JP 10050481 A	20-02-1998
JP 2000173777	A	23-06-2000	NONE	
JP 10270173 7	A		NONE	
EP 0880303	A	25-11-1998	JP 10153967 A	09-06-1998
			DE 69727212 D1	19-02-2004
			EP 0880303 A1	25-11-1998
			CN 1212114 A ,C	24-03-1999
			EP 1211916 A1	05-06-2002
			EP 1376716 A2	02-01-2004
			EP 1376717 A2	02-01-2004
			WO 9824271 A1	04-06-1998
			TW 553579 Y	11-09-2003
			US 2003054186 A1	20-03-2003
			US 2002155215 A1	24-10-2002
			US 2001001050 A1	10-05-2001
			US 2002136823 A1	26-09-2002
			US 2002041926 A1	11-04-2002
EP 1103590	A	30-05-2001	JP 2001155861 A	08-06-2001
			JP 2001155858 A	08-06-2001
			EP 1103590 A2	30-05-2001
			US 6582504 B1	24-06-2003
EP 1195736	A	10-04-2002	US 6424093 B1	23-07-2002
			EP 1195736 A2	10-04-2002
			JP 2002164173 A	07-06-2002
JP 07335383 7	A		NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.